

BS ISO 4381:2011



BSI Standards Publication

# Plain bearings — Tin casting alloys for multilayer plain bearings

NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW

*raising standards worldwide™*



**National foreword**

This British Standard is the UK implementation of ISO 4381:2011. It supersedes BS ISO 4381:2000 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee MCE/12, Plain bearings.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2012

ISBN 978 0 580 73558 5

ICS 21.100.10; 77.120.60

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 January 2012.

**Amendments issued since publication**

| Date | Text affected |
|------|---------------|
|------|---------------|

---

# INTERNATIONAL STANDARD

BS ISO 4381:2011

**ISO**  
**4381**

Fourth edition  
2011-11-01

---

---

## Plain bearings — Tin casting alloys for multilayer plain bearings

*Paliers lisses — Alliages moulés à base d'étain pour paliers lisses  
multicouches*



Reference number  
ISO 4381:2011(E)

© ISO 2011



## **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2011

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

|  |           |
|--|-----------|
| <b>Foreword</b> .....  | <b>iv</b> |
| <b>1 Scope</b> .....   | <b>1</b>  |
| <b>2 Normative references</b> .....  | <b>1</b>  |
| <b>3 Requirements</b> .....  | <b>1</b>  |
| <b>3.1 Chemical composition</b> .....  | <b>1</b>  |
| <b>3.2 Material properties</b> .....   | <b>1</b>  |
| <b>3.3 Selection of material</b> .....   | <b>1</b>  |
| <b>4 Designation</b> .....   | <b>3</b>  |
| <b>Annex A (informative) Guidance on use of bearing metals and the hardness of the mating bearing part (shaft)</b> ..... | <b>4</b>  |
| <b>Bibliography</b> .....  | <b>5</b>  |

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 4381 was prepared by Technical Committee ISO/TC 123, *Plain bearings*, Subcommittee SC 2, *Materials and lubricants, their properties, characteristics, test methods and testing conditions*.

This fourth edition cancels and replaces the third edition (ISO 4381:2000), which has been technically revised.

# Plain bearings — Tin casting alloys for multilayer plain bearings

## 1 Scope

This International Standard specifies requirements for bearing metals based on tin casting alloys for multilayer plain bearings. The chemical composition and material properties refer to the original unprocessed material and are measured on representative samples. Testing results on final bearings can differ due to the influence of bearing production. Therefore, it is not intended that these results be compared with data given in this International Standard.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1143, *Metallic materials — Rotating bar bending fatigue testing*

ISO 4384-2, *Plain bearings — Hardness testing of bearing metals — Part 2: Solid materials*

ISO 4386-2:—<sup>1)</sup>, *Plain bearings — Metallic multilayer plain bearings — Part 2: Destructive testing of bond for bearing metal layer thicknesses greater than or equal to 2 mm*

## 3 Requirements

### 3.1 Chemical composition

The chemical composition of alloy elements shall be within the limits specified in Table 1. The chemical analysis is decisive for the acceptance of the bearing metals.

### 3.2 Material properties

Material properties shall be in accordance with the data given in Table 1.

All material property values are mean values or ranges and are regarded as typical values for the designer. In view of the range of possible alloy compositions and the marked influence exerted by the cooling conditions on the mechanical properties, relatively large deviations from the indicated values are to be expected in individual cases.

### 3.3 Selection of material

Guidance on uses of bearing metals and on the hardness of the mating bearing part (shaft) is given in Annex A.

---

1) Under preparation.

Table 1 — Tin casting alloy

| Chemical element  | Chemical composition, mass fraction |   |
|---|-------------------------------------|---|
|   | %                                   |   |
|   | SnSb8Cu4                            |   |
| Sn  | Remainder                           |   |
| Sb  | 7 to 8                              |   |
| Cu  | 3 to 4                              |   |
| Impurities  |                                     |   |
| Pb  | <0,35                               |   |
| As  | <0,1                                |   |
| Bi  | <0,08                               |   |
| Fe  | <0,1                                |   |
| Al  | <0,01                               |   |
| Zn  | <0,01                               |   |
| Cd  | <0,05                               |   |
| Total others  | 0,2                                 |   |
| Material properties   |                                     |   |
| Brinell hardness<br>in accordance with ISO 4384-2<br>HBW 10/250/180   | 20 °C                               | 22  |
|   | 100 °C                              | 10  |
| 0,2 % tensile yield stress<br>$R_{p0,2}$<br>N/mm <sup>2</sup>   | 20 °C                               | 46  |
| Tensile strength<br>$R_m$<br>N/mm <sup>2</sup>  | 20 °C                               | 77  |
| 0,2 % compressive yield stress<br>$\sigma_{d0,2}$<br>N/mm <sup>2</sup>  | 20 °C                               | 47  |
|   | 100 °C                              | 27  |
| Bond strength<br>$R_{Ch}$<br>N/mm <sup>2</sup>  |                                     | In accordance with ISO 4386-2:—, 8.1 and 8.2. |
| Rotating bar bending fatigue<br>$R_{rbf}$<br>in accordance with ISO 1143<br>10 <sup>7</sup> cycles, N/mm <sup>2</sup> |                                     | ± 29  |
| Linear thermal expansion<br>coefficient, $\alpha_l$<br>10 <sup>-6</sup> /K  |                                     | 23,9  |
| Melting temperature<br>°C   |                                     | 233 to 360                                    |
| Casting temperature<br>°C   |                                     | 440 to 460                                    |
| Density, $\rho$<br>kg/dm <sup>3</sup>   |                                     | 7,3   |



## 4 Designation

EXAMPLE A bearing metal having the chemical composition indicated by the symbol SnSb8Cu4 is designated as follows:

**Bearing metal ISO 4381 — SnSb8Cu4**

**Annex A**  
 (informative)

**Guidance on use of bearing metals and the hardness of the mating bearing part (shaft)**

| Bearing alloy   | Characteristics and principal uses  | Minimum hardness of the shaft <sup>a</sup> |
|---|---|--|
| <b>SnSb8Cu4</b>   | <p>Good sliding properties, conformability and high toughness; good embeddability; suitable for high sliding velocities in the hydrodynamic range, mean load; impact stress at low frequency; insensitive to reversed bending stress.</p> <p>Used for high loaded rolling mill bearings; for the production of wrapped bushes, thin-walled bearing liners with a wall thickness of up to about 3 mm and thrust washers.</p> | 160 HB                                     |
| <p><sup>a</sup> In multilayer plain bearings, the difference between the hardness of the bearing material and the shaft material should be such that welding under working conditions is safely avoided. The working conditions, in particular the lubrication conditions, have considerable influence on the selection of the shaft material. For this reason, the recommended hardness value for the shaft material is a minimum value. In general, unquenched and untempered shaft materials are used in the case of bearing materials based on tin.</p> |   |  |

Licensed copy: I P, The University of Leeds, Version correct as of 10/04/2013 17:36, (c) The British Standards Institution 2013

## Bibliography

- [1] ISO 4386-1, *Plain bearings — Metallic multilayer plain bearings — Part 1: Non-destructive ultrasonic testing of bond*
- [2] ISO 4386-3, *Plain bearings — Metallic multilayer plain bearings — Part 3: Non-destructive penetrant testing*

---

---

**ICS 21.100.10; 77.120.60**

Price based on 5 pages



# British Standards Institution (BSI)

BSI is the independent national body responsible for preparing British Standards and other standards-related publications, information and services. It presents the UK view on standards in Europe and at the international level.

BSI is incorporated by Royal Charter. British Standards and other standardisation products are published by BSI Standards Limited.

## Revisions

British Standards and PASs are periodically updated by amendment or revision. Users of British Standards and PASs should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using British Standards would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Similar for PASs, please notify BSI Customer Services.

**Tel: +44 (0)20 8996 9001 Fax: +44 (0)20 8996 7001**

BSI offers BSI Subscribing Members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of British Standards and PASs.

**Tel: +44 (0)20 8996 7669 Fax: +44 (0)20 8996 7001**

**Email: [plus@bsigroup.com](mailto:plus@bsigroup.com)**

## Buying standards

You may buy PDF and hard copy versions of standards directly using a credit card from the BSI Shop on the website [www.bsigroup.com/shop](http://www.bsigroup.com/shop). In addition all orders for BSI, international and foreign standards publications can be addressed to BSI Customer Services.

**Tel: +44 (0)20 8996 9001 Fax: +44 (0)20 8996 7001**

**Email: [orders@bsigroup.com](mailto:orders@bsigroup.com)**

In response to orders for international standards, BSI will supply the British Standard implementation of the relevant international standard, unless otherwise requested.

## Information on standards

BSI provides a wide range of information on national, European and international standards through its Knowledge Centre.

**Tel: +44 (0)20 8996 7004 Fax: +44 (0)20 8996 7005**

**Email: [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)**

BSI Subscribing Members are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.

**Tel: +44 (0)20 8996 7002 Fax: +44 (0)20 8996 7001**

**Email: [membership@bsigroup.com](mailto:membership@bsigroup.com)**

Information regarding online access to British Standards and PASs via British Standards Online can be found at [www.bsigroup.com/BSOL](http://www.bsigroup.com/BSOL)

Further information about British Standards is available on the BSI website at [www.bsi-group.com/standards](http://www.bsi-group.com/standards)

## Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that own copyright in the information used (such as the international standardisation bodies) has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained. Details and advice can be obtained from the Copyright & Licensing Department.

**Tel: +44 (0)20 8996 7070**

**Email: [copyright@bsigroup.com](mailto:copyright@bsigroup.com)**

## BSI

389 Chiswick High Road London W4 4AL UK

Tel +44 (0)20 8996 9001

Fax +44 (0)20 8996 7001

[www.bsigroup.com/standards](http://www.bsigroup.com/standards)